

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
15 August 2002 (15.08.2002)

PCT

(10) International Publication Number  
**WO 02/062890 A1**

- (51) International Patent Classification<sup>7</sup>: C08L 33/12 // (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (21) International Application Number: PCT/US02/03644
- (22) International Filing Date: 6 February 2002 (06.02.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
60/266,642 6 February 2001 (06.02.2001) US
- (71) Applicant (*for all designated States except US*): CYRO INDUSTRIES [US/US]; 100 Enterprise Drive, Rockaway, NJ 07866-5055 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): COLBURN, Peter, D., Jr. [US/US]; 57 Meadow Hill Drive, Guilford, CT 06437 (US). DIMOV, Dimo, K. [BG/US]; 255 Brushy Plain Road, Bransford, CT 06405 (US). CAPRILES, Edward [US/US]; 64 Spindrift Lane, Guilford, CT 06437 (US).
- (74) Agent: JACKSON, David, A.; Klauber & Jackson, 411 Hackensack Avenue, Hackensack, NJ 07601 (US).
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report  
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: POLYMETHYLMETHACRYLATE COMPOSITIONS OF ENHANCED OPTICS AND LOW TEMPERATURE IMPACT STRENGTH

(57) Abstract: Acrylic based multipolymer compositions having enhanced optical properties, comparable to impact modified PMMA resins, good sub-zero temperature impact strength similar to that of the Acrylic Based Multipolymer Compounds and improved weatherability, are disclosed. These compositions comprise a blend of an acrylic based multipolymer, comprising one or more of acrylonitrile, butyl acrylate, ethyl acrylate, methyl acrylate, methyl methacrylate, and styrene; a methylmethacrylate-butadiene-styrene (MBS) copolymer modifier polymerized by a free radical process; UV stabilizers, including benzotriazole derivatives, triazine derivatives, and hindered amine light stabilizers, as single components or combinations thereof; and one or more antioxidants, dyes and plasticizing flow enhancers. Both the compositions and their method of preparation are disclosed. The compositions are particularly useful for injection molding applications and the preparation of polymer films and sheets having improved optical and thermal properties, that are particularly suited for a variety of industrial applications.

WO 02/062890 A1

## POLYMETHYLMETHACRYLATE COMPOSITIONS OF ENHANCED OPTICS AND LOW TEMPERATURE IMPACT STRENGTH

BACKGROUND OF THE INVENTION

5

Field of the Invention

The present invention relates to the preparation and use of acrylic based compounds for injection molding applications and the preparation of polymer films and sheets having improved optical and thermal properties, that are particularly suited for a variety of industrial applications.

Description of the Related Art

15 Polymethylmethacrylate (PMMA) resins are well known for their exceptional clarity and good weatherability and find applications such as automotive, glazing, packaging, etc. The impact properties of these polymers have been improved by blending butyl acrylate impact modifiers polymerized by free radical emulsion polymerization. However, impact modified PMMA resins generally possess relatively poor impact properties at sub-zero temperatures, thereby limiting their use in this temperature range.

Acrylic based multipolymer compounds, like Acrylite XT® polymer & CYROLITE® are impact modified with polybutadiene modifiers and retain high level of impact strength at substantially lower temperatures than the corresponding PMMA grades, *i.e.* -80°F.

25 However, the optical properties of state of the art polybutadiene modified resins is deficient relative to the optics of PMMA resins.

Accordingly, a need exists for an improved class of resin compounds and compositions that offer improved thermal and optical properties and performance in a broad range of environmental conditions.

5

### SUMMARY OF THE INVENTION

The present invention provides acrylic based multipolymer compositions having enhanced optical properties, comparable to impact modified PMMA resins, good sub-zero temperature impact strength similar to that of the Acrylic Based Multipolymer  
10 Compounds, like XT® polymer & CYROLITE®, and improved weatherability. These compositions comprise a blend of:

15 A) an acrylic based multipolymer, comprising in weight %: 8-12% acrylonitrile, 3-8% butyl acrylate, 3-5% ethyl acrylate, 3-8% methyl acrylate, 65-80% methyl methacrylate, and 15-30% styrene.

B) a methylmethacrylate-butadiene-styrene (MBS) copolymer modifier polymerized by a free radical process.

20 C) commercially available UV stabilizers, including benzotriazole derivatives, triazine derivatives, and hindered amine light stabilizers, as single components or combinations thereof.

25 D) a combination of commercially available antioxidants, dyes and plasticizing flow enhancers.

In a particular embodiment, the composition comprises, in weight percent, from 55 to 85% of component A, from 15 to 45% of component B, up to about 0.5% of component C, and up to 5.0% of component D.

More particularly, the invention extends to such compositions displaying the combination of improved optical properties and sub-zero temperature stability, that are prepared by a method that includes the blending of components to achieve a Refractive Index (RI) that tolerates a maximum mismatch between components of 0.001 refractive index units.

5

In a further aspect, the invention relates to an acrylic based multipolymer composition wherein the auxiliary polymer additives have composition within the following range, in % by weight:

10	Formula A, low refractive index:	methyl methacrylate	92-98%
		methyl acrylate	2-8%
	Formula B, high refractive index	methyl methacrylate	30-50%
		styrene	45-70%
		acrylonitrile	8-12%
		ethyl acrylate	3-8%

15

The inventive compositions may include up to 5% of lubricants, processing aids, and plasticisers. Further the compositions may contain up to 0.5% of UV stabilizers, and such stabilizers may in turn, comprise benzotriazole derivatives, including benzotriazole derivatives selected from the group consisting of 2-(2'-hydroxy-5'-methylphenyl)

20 benzotriazole, triazine derivatives, *e.g.* 2-(4,6-diphenyl-1,3,5-triazine-2-yl)-5-hexyloxy)phenol, or hindered amine light stabilizers, and combinations thereof.

As stated above and herein, the compositions of of the invention exhibit the retention of room temperature impact strength tdo a commercially significant level at sub-zero  
25 temperatures, as low as -80°F. Accordingly, numerous formed products may be prepared that take advantage of the mechanical and optical properties exhibited by the present compositions.

Other objects and advantages will become apparent to those skilled in the art from a

consideration of the detailed description that proceeds with reference to the following illustrative drawings.

### BRIEF DESCRIPTION OF THE DRAWINGS

5

Figures 1 and 2 and TEM micrographs of the impact modified acrylic based resin of Example 1.

### DETAILED DESCRIPTION OF THE INVENTION

10

The improved impact strength of the products is due to microphase separation of the polymer blend, the particle size of the rubber phase being a critical factor in control of the underlying fracture mechanics. A suitable particle size range is from at least about 50 nanometers (nm) and can be on the order of 100 nm or more.

15

The small size modifier particles in the hard phase as seen in TEM micrographs (Figures 1 and 2), the good mechanical properties like impact strength, ductility (*i.e.* elongation at break), as well as other key properties which would be adversely affected in an incompatible alloy/blend, all suggest a favorable compatibility of the MBS modifier with the multipolymer matrix. The reason why clarity is maintained is because of refractive index matching between the modifier and the hard phase. The common methods of monomer blend composition control do not provide access to the range of 0.001 refractive index units, critical for the target optical properties. In the present invention, this high level of accuracy is achieved by a process of controlled feeding of auxiliary polymer additives that have different refractive index from and are miscible with the multipolymer hard phase.

20

25

It is possible to modify the Refractive Index (RI) of transparent acrylic plastics by means of mechanical blends of polymers of varying RI's. This can be used for RI adjustment of

the acrylic resin to the target RI of the impact modifier. The method is useful in the following cases:

- Compensation for process variation of acrylic resin RI
- Compensation for impact modifier RI
- 5 Compensation for impact modifier RI changes due to extruder condition changes

Incompatibility is a common phenomenon in polymers and results in microphase separated opaque polymer blends. Miscibility of the polymer components of the matrix material is critical for the optical clarity in the current applications. For this reason, the auxiliary resins for RI adjustment are carefully designed to be completely miscible with the acrylic resin. They are acrylonitrile/styrene/acrylic copolymers of varied composition tuned to the desired refractive indices. The blends are prepared by feeding an extruder with precision loss-in-weight feeders which control the ratio of the base polymer and the RI modifying polymer. The overall RI can be approximated to the sum of RI contributions proportional to the volume fractions of the individual polymer components. Experimental work has shown that with proper comonomer selection, the RI of the basic acrylic resin can be adjusted within a relatively broad range, *i.e.*, 1.49 to 1.60. Particular examples of procedures for polymer preparation and processing that seeks to optimize RI match of the components, are set forth below.

20

In a first example, the base acrylic polymer is intentionally modified to optimize the RI match to the impact modifier. A 6" diameter Welding Engineers, non-intermeshing, counter rotating, 36/L/D devolatilizing extruder was fed with an acrylic copolymer and impact modifier. The polymer was fed with a LUWA Vacurex 110/110 metering pump and the modifier with an Acrison 403 Loss-In-Weight (LIW) feeder with micro-date control. A portable Acrison 403 LIW was used to feed acrylic copolymers of high and low RI's optimizing the RI match.

25

A second example of this technique was carried out using a 50/1 L/D, 4-1/2" two stage,

single double wave screw compounder. Three Technetic LIW feeders were used, one for the impact modifier, the second for the base acrylic copolymer and the third a tumble blend of the base polymer, additives and the RI modifying acrylic copolymer. This again, allowed an optimization of the RI match between the various phases.

5

Novel Features: A combination of optical clarity surpassing the optical properties of conventional polybutadiene impact modified acrylic compounds and retained impact strength at sub-zero temperatures, with particular strength measured at about 1 to 2 foot-pounds per inch.

10

Utility of Invention: Improved appearance and color due to enhanced optical clarity. Applications in wider temperature range, as low as -80°F.

15

The present invention will be better understood from a consideration of the following illustrative examples presenting formulations and their properties and characteristics, it being understood that the following are illustrative and not restrictive, and that all percentages are expressed in weight unless otherwise specified.

20

### EXAMPLES

The following compositions were prepared for use in the preparation of formed products that could be tested for optical and impact properties.

25

<u>Formulation 1:</u>	Terpolymer of methyl methacrylate, styrene and	
	Ethyl acrylate	64.25%
	Kane-Ace B-564, supplied by Kaneka Texas Corp.	35%
	Plasticizing agent, stearyl alcohol	0.4%
	Antioxidant, Irgafos 168 powder	0.2%

30

UV stabilizing agent, Tinuvin P 0.15%

Colorants for color matching, proprietary composition

5 Formulation 2: Commercially available impact modified acrylic molding and extrusion compounds, comprising polymethylmethacrylate, methyl acrylate, and butyl acrylate, with a BA modifier comprising methyl methacrylate, butyl acrylate and styrene, with a representative composition commercially available as ACRYLITE PLUS® ZK-6 by CYRO Inds.

10 Formulation 3: Commercially available impact modified acrylic molding and extrusion compounds, comprising polymethylmethacrylate, ethyl acrylate and styrene, and a MBS modifier comprising methyl acrylate, styrene and butadiene, with a representative composition commercially available as CYROLITE G-20 HIFLO® by CYRO Inds.

The above formulations were used to prepare formed samples for testing as to optical and mechanical properties. The tests were conducted in accordance with known industry standards (ASTM), and the results are set forth in Table I, below.

TABLE I

	<u>ASTM Test</u>	<u>#1</u>	<u>#2</u>	<u>#3</u>
25 <u>Optical Properties</u>				
- Transmittance (%)	D1003	91	91.5	89
- Haze (%)	D1003	1.1	1.0	3.5
- Yellowness Index	D1003	-2.0	0.4	-0.5
30 <u>Mechanical Properties</u>				
- Tensile Strength, psi	D 638	5500	6800	7,000
- Tensile Modulus, psi	D 638	240000	260000	370000
- Tensile Elongation				



	@ Yield (%)	D 638	4.0	5.0	3.8
	@ Break (%)	D 638	35	50	9.5
	- Notched Izod, ft-lb/in				
	1/4"bar @ 23°C	D 256	1.5	1.0	1.9
5	1/4"bar @ 0°C	D 256	1.2	0.6	1.1
	1/4"bar @ -32°C	D 256	1.0	-	-
	-Rockwell Hardness (L)	D 785	45	35	27

#### Rheological Properties

10	- Melt Flow Index, g/10 min				
	@230°C, 5.0 kg	D1238	9	-	12
	@230°C, 3.8 kg	D1238	-	1.6	-

#### 15 B. Examples of applications

Acrylic based multipolymer molding and extrusion compositions may be prepared with particular ingredients and in the range of percentages as stated in claims (7), (8), (9), (10), (11), and (12) which are used in applications requiring toughness and transparency at low  
 20 temperatures, including transparent mechanical tool handles; transparent refrigerator bins, shelves, or doors; medical filter housings; IV connectors; medical storage or treatment trays; dental treatment device handles; and commercial display shelves and components.

#### 25 C. Chemical Compositions

Component A: acrylic based multipolymer as described above.

Component B: a high rubber graft copolymer, wherein said graft copolymer may  
 30 comprise:

- from 50 to 95 percent by weight of a conjugated diene polymeric substrate having a glass transition temperature below -60° C. An exemplary resin is an emulsion polymer of 1,3-butadiene.

- from 5 to 50 percent by weight of a rigid superstrate copolymer having a glass

transition temperature greater than or equal to 50°C and consisting essentially of repeating units of a vinyl aromatic monomer and one or more (C<sub>1</sub> - C<sub>12</sub>) alkyl (meth)acrylate monomers, wherein at least a portion of the rigid superstrate is grafted onto the diene polymeric substrate. An exemplary grafted shell is the copolymer of  
5 methyl methacrylate and styrene with a low content of a cross-linking agent.

Components C&D: UV stabilizers, antioxidants, dyes etc. These are conventional additives used to enhance processability and certain performance parameters.

- 10 This invention may be embodied in other forms or carried out in other ways without departing from the spirit or essential characteristics thereof. The present disclosure is therefore to be considered as in all respects illustrative and not restrictive, the scope of the invention being indicated by the appended Claims, and all changes which come within the meaning and range of equivalency are intended to be embraced therein.

15

WHAT IS CLAIMED IS:

1. An acrylic based multipolymer molding and extrusion composition possessing improved optical properties and low temperature impact resistance, comprising:
  - 5 A) an acrylic based multipolymer, comprising in weight %: 8-12% acrylonitrile, 3-8% butyl acrylate, 3-5% ethyl acrylate, 3-8% methyl acrylate, 65-80% methyl methacrylate, and 15-30% styrene, said multipolymer present in an amount of from 55 to 85% by weight;
  - B) a methylmethacrylate-butadiene-styrene (MBS) copolymer modifier  
10 polymerized by a free radical process, said MBS copolymer modifier present in an amount of from 15 to 45% by weight;
  - C) a UV stabilizer, selected from the group consisting of benzotriazole derivatives, triazine derivatives, and hindered amine light stabilizers, and combinations thereof, said UV stabilizer present in an amount of up to about 0.5% by weight; and  
15 D) one or more additives including antioxidants, dyes and plasticizing flow enhancers, such additives present in an amount of up to 5.0% by weight;wherein said composition also possesses improved room temperature impact strength and optical clarity similar to that of unmodified acrylic resins.
- 20 2. The composition of Claim 1, wherein the MBS impact modifier is comprised of several monomers within the following composition range, in % by weight: 50-90% 1,3-butadiene, 5-45% methyl methacrylate, and 3-15% styrene.
3. A process for preparing an acrylic based multipolymer molding and extrusion  
25 composition which comprises controlled feeding of auxiliary polymer additives that have different refractive indices from and are miscible with the multipolymer hard phase, to adjust the refractive index of the multipolymer hard phase to within 0.001 units and preferably 0.0005 units of the refractive index of the MBS modifier.

4. A process as in Claim 3, wherein the compounding of the MBS modifier into the multipolymer hard phase and the feeding of the auxiliary polymers occurs in a single extrusion step.
5. An acrylic based multipolymer molding and extrusion composition as in either of Claims 1 or 2, prepared with refractive index matching using auxiliary polymer additives, wherein the refractive index of the multipolymer hard phase is within about 0.001 units of the refractive index of the MBS modifier.
6. The composition of Claim 5, wherein the auxiliary polymer additives have composition within the following range, in % by weight:
- |                                  |                     |        |
|----------------------------------|---------------------|--------|
| Formula A, low refractive index: | methyl methacrylate | 92-98% |
|                                  | methyl acrylate     | 2-8%   |
| Formula B, high refractive index | methyl methacrylate | 30-50% |
|                                  | styrene             | 45-70% |
|                                  | acrylonitrile       | 8-12%  |
|                                  | ethyl acrylate      | 3-8%   |
7. The composition of Claims 5 or 6, containing up to 5% of lubricants, processing aids, and plasticisers.
8. The composition of Claims 5 or 6, containing up to 0.5% of UV stabilizers.
9. The composition of Claim 8, where the UV stabilizers are benzotriazole derivatives.
10. The composition of Claim 9, wherein said benzotriazole derivatives are selected from the group consisting of 2-(2'-hydroxy-5'-methylphenyl) benzotriazole, triazine derivatives, e.g. 2-(4,6-diphenyl-1,3,5-triazine-2-yl)-5-hexyloxy)phenol, hindered amine

light stabilizers, and combinations thereof.

11. The composition of any of Claims 5-9 or 10, where the room temperature impact strength is retained to a commercially significant level at sub-zero temperatures, as low as  
5 -80°F.

12. An acrylic based multipolymer molding and extrusion composition possessing improved optical properties and low temperature impact resistance, comprising:

- A) an acrylic based multipolymer, comprising a terpolymer of methyl  
10 methacrylate, styrene and ethyl acrylate in an amount of 64.25% by weight;  
B) a methylmethacrylate-butadiene-styrene (MBS) copolymer modifier polymerized by a free radical process, said MBS copolymer modifier present in an amount of 35% by weight;  
C) an antioxidant in an amount of up to about 0.4% by weight; and  
15 D) a plasticizing agent in an amount of 0.4% by weight;  
wherein said composition also possesses improved room temperature impact strength and optical clarity similar to that of unmodified acrylic resins.

13. The composition of either of Claims 1 or 12, wherein the composition contains a  
20 rubber phase, and the average particle size of said rubber phase is at least 50 nm.

14. The composition of either of Claims 1 or 12, wherein the composition contains a rubber phase, and the average particle size of said rubber phase is on the order of about  
100 nm.

25




Figure 1




Figure 2

## INTERNATIONAL SEARCH REPORT

Inte al Application No

PC 1 / US 02/03644

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L33/12 //(C08L33/12,51:04)

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR 1 221 378 A (ROHM & HAAS) 1 June 1960 (1960-06-01) page 4, right-hand column, line 7 - line 15; claims	1
A	GB 2 030 154 A (AMERICAN CYANAMID CO) 2 April 1980 (1980-04-02) claims; examples 1-40	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*Z\* document member of the same patent family

Date of the actual completion of the international search

1 July 2002

Date of mailing of the international search report

10/07/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Schueler, D



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/03644

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
FR 1221378	A	01-06-1960	BE 577102 A	
			CH 417089 A	15-07-1966
			DE 1256413 B	14-12-1967
			GB 845638 A	24-08-1960
			NL 111970 C	
			NL 237495 A	
<hr/>				
GB 2030154	A	02-04-1980	US 4228256 A	14-10-1980
			US 4242469 A	30-12-1980
			CA 1126432 A1	22-06-1982
			DE 2937718 A1	27-03-1980
			FR 2455066 A1	21-11-1980
			FR 2491930 A1	16-04-1982
			FR 2491931 A1	16-04-1982
			GB 2106914 A ,B	20-04-1983
			GB 2106120 A ,B	07-04-1983
			GB 2107329 A ,B	27-04-1983
			JP 1586692 C	19-11-1990
			JP 2002902 B	19-01-1990
			JP 55040794 A	22-03-1980
			JP 2138323 A	28-05-1990
			CA 1134092 A1	19-10-1982
<hr/>				